

TABLES USED FOR CONCRETE MIX DESIGN (CSA A23.1)

The following tables are those of chapter 9 of “Design and Control of Concrete Mixtures” published by the Cement Association of Canada (7th edition).

Table 9-1. Maximum Water-Cementing Materials Ratios and Minimum Design Strengths for Various Exposure Conditions*

Requirements for specifying concrete	Requirements for concrete		
Class of Exposure*	Maximum water-to-cementing materials ratio	Minimum, specified 28-day compressive strength, MPa	Air content category
C-1	0.40	35	**
C-2	0.45	32	1
C-3	0.50	30	2
C-4	0.55	25	2
F-1	0.50	30	1***
F-2	0.55	25	2***
N	For structural design	For structural design	

* See Table 8-2 or this Chapter for a description of classes of exposure.

** Use Category 1 for concrete exposed to freezing and thawing.

Use Category 2 for concrete not exposed to freezing and thawing.

*** Interior ice rink slabs and freezer slabs with a steel-troweled finish have been found to perform satisfactorily without entrained air.

Source: CSA Standard A23.1.

Table 9-2. Requirements for Concrete Subjected to Sulphate Attack*

Class of exposure	Degree of exposure	Water-soluble sulphate (SO ₄) in soil sample, %	Sulphate (SO ₄) in groundwater samples, mg/L	Minimum specified 56-day compressive strength, MPa†	Maximum water-to-cementing materials ratio‡	Air content category▲	Cementing materials to be used***
S-1	Very severe	Over 2.0	Over 10,000	35	0.40	2	50
S-2	Severe	0.20 – 2.0	1500 – 10,000	32	0.45	2	50
S-3	Moderate	0.10 – 0.20	150 – 1500	30	0.50	2	20E‡‡, 40, or 50E

* For seawater exposure refer to CSA A23.1, Clause 15.

† Where supplementary cementing materials are used, the owner may specify other test ages.

‡ The owner shall specify the minimum 28-day compressive strength.

** When combinations of portland cement and supplementary cementing materials are used, they shall have been proven, to the satisfaction of the owner, to produce concrete resistant to the exposure conditions under consideration.

▲ For steel-troweled interior slabs on grade, subject to sulphate attack but not freeze thaw, air entrainment is not required.

†† Cementing material combinations with equivalent performance may be used. (Refer to CSA A23.1, Clauses 3.2, 3.3, and 3.4).

‡‡ Type 20E cement with moderate sulphate resistance (Refer to CSA A23.1, Clause 3.1.2).

Note: Type 50E cement shall not be used in reinforced concrete exposed to both chlorides and sulphates.

Refer to CSA A 23.1, Clause 15.4.

See CSA Test Methods A23.2-2B and A23.2-3B for test methods to determine sulphate ion content.

Source: CSA Standard A23.1

Table 9-3. Relationship Between Water to Cementing Materials Ratio and Compressive Strength of Concrete

Compressive strength at 28 days, MPa	Water-cementing materials ratio by mass	
	Non-air-entrained concrete	Air-entrained concrete
45	0.38	0.30
40	0.42	0.34
35	0.47	0.39
30	0.54	0.45
25	0.61	0.52
20	0.69	0.60
15	0.79	0.70

Strength is based on cylinders moist-cured 28 days in accordance with CSA A23.2-3C (ASTM C 31). Relationship assumes nominal maximum size aggregate of about 20 to 28 mm. Adapted from ACI 211.1 and ACI 211.3.

Table 9-4. Bulk Volume of Coarse Aggregate Per Unit Volume of Concrete

Nominal maximum size of aggregate, mm	Bulk volume of dry-rodded coarse aggregate per unit volume of concrete for different fineness moduli of fine aggregate*			
	2.40	2.60	2.80	3.00
10	0.50	0.48	0.46	0.44
14	0.59	0.57	0.55	0.53
20	0.66	0.64	0.62	0.60
28	0.71	0.69	0.67	0.65
40	0.75	0.73	0.71	0.69
56	0.78	0.76	0.74	0.72
80	0.82	0.80	0.78	0.76
150	0.87	0.85	0.83	0.81

*Bulk volumes are based on aggregates in dry-rodded condition as described in CSA A23.2-10A (ASTM C 29). Adapted from ACI 211.1.

Table 9-5. Approximate Mixing Water and Air Content Requirements for Different Slumps and Nominal Maximum Sizes of Aggregate

Slump, mm	Water, kilograms per cubic metre of concrete, for indicated sizes of aggregate*							
	10 mm	14 mm	20 mm	28 mm	40 mm	56 mm**	80 mm**	150 mm**
Non-air-entrained concrete								
25 to 50	207	199	190	179	166	154	130	113
75 to 100	228	216	205	193	181	169	145	124
150 to 175	243	228	216	202	190	178	160	—
Approximate amount of entrapped air in non-air-entrained concrete, percent	3	2.5	2	1.5	1	0.5	0.3	0.2
Air-entrained concrete								
25 to 50	181	175	168	160	150	142	122	107
75 to 100	202	193	184	175	165	157	133	119
150 to 175	216	205	197	184	174	166	154	—
CSA A23.1 Recommended total air content percent†	6 to 9	5 to 8		4 to 7		—	—	—
Category 1	5 to 8	4 to 7		3 to 6		—	—	—
Category 2								

* These quantities of mixing water are for use in computing cementing material contents for trial batches. They are maximums for reasonably well-shaped angular coarse aggregates graded within limits of accepted specifications.

** The slump values for concrete containing aggregates larger than 40 mm are based on slump tests made after removal of particles larger than 40 mm by wet screening.

† See Tables 9-1 and 9-2 for class of exposure and corresponding air content category.

Adapted from CSA Standard A23.1, ACI 211.1, and ACI 318. Hover (1995) presents this information in graphical form.

Table 9-6. Recommended Slumps for Various Types of Construction

Concrete construction	Slump, mm	
	Maximum*	Minimum
Reinforced foundation walls and footings	75	25
Plain footings, caissons, and substructure walls	75	25
Beams and reinforced walls	100	25
Building columns	100	25
Pavements and slabs	75	25
Mass concrete	75	25

*May be increased 25 mm for consolidation by hand methods, such as rodding and spading.
 Plasticizers can safely provide higher slumps.
 Adapted from ACI 211.1.

Table 9-7. Minimum Requirements of Cementing Materials for Concrete Used in Flatwork

Nominal maximum size of aggregate, mm	Cementing materials, kg/m ³ *
40	280
28	310
20	320
14	350
10	360

*Cementing materials quantities may need to be greater for severe exposure. For example, for deicer exposures, concrete should contain at least 335 kg/m³ of cementing materials.
 Adapted from ACI 302.

Table 9-8. Cementing Materials Requirements for Concrete Exposed to Deicing Chemicals

Cementing materials*	Maximum percent of total cementing materials by mass**
Fly ash and natural pozzolans	25
Slag	50
Silica fume	10
Total of fly ash, slag, silica fume and natural pozzolans	50†
Total of natural pozzolans and silica fume	35†

* Includes portion of supplementary cementing materials in blended cements.

** Total cementing materials include the summation of portland cements, blended cements, fly ash, slag, silica fume and other pozzolans.

† Silica fume should not constitute more than 10% of total cementing materials and fly ash or other pozzolans shall not constitute more than 25% of cementing materials.

Adapted from ACI 318.

Table 9-9. Maximum Chloride-Ion Content for Corrosion Protection

Type of member	Maximum water-soluble chloride ion (Cl⁻) in concrete, percent by mass of cementing material
Prestressed concrete	0.06
Reinforced concrete exposed to a moist environment or chlorides or both	0.15
Reinforced concrete exposed to neither a moist environment nor chlorides	1.00

Source: CSA Standard A23.1

Table 9-10. Modification Factor for Standard Deviation When Less Than 30 Tests Are Available

Number of tests*	Modification factor for standard deviation**
Less than 15	Use Table 9-11
15	1.16
20	1.08
25	1.03
30 or more	1.00

* Interpolate for intermediate numbers of tests.

** Modified standard deviation to be used to determine required average strength, f'_{cr} .

Adapted from ACI 318.

Table 9-11. Required Average Compressive Strength When Data Are Not Available to Establish a Standard Deviation

Specified compressive strength, f'_c , MPa	Required average compressive strength, f'_{cr} , MPa
Less than 21	$f'_c + 7.0$
21 to 35	$f'_c + 8.5$
Over 35	$f'_c + 10.0$

Adapted from ACI 318.

$$f'_{cr} = f'_c + 1.4 S$$

$$f'_{cr} = f'_c + (2.4 S - 3.5 \text{ MPa})$$

Table 8-2. Exposure Classes

CSA A23.1

C-1	Structurally r.c. exposed to Cl w/ or w/o freezing & thawing (bridge decks, parking decks & ramps, ...)
C-2	Non-structurally r.c. (plain) exposed to Cl & freezing & thawing (garage floors, sidewalks, steps, curbs, ...)
C-3	Submerged concrete exposed to Cl but not freezing & thawing (underwater portions of marine structures)
C-4	Non-structurally r.c. exposed to Cl but not freezing & thawing (underground parking slabs on grade)
F-1	Saturated concrete exposed to freezing & thawing but not to Cl (pool decks, patios, freshwater control structures)
F-2	Unsaturated concrete exposed to freezing & thawing but not to Cl (exterior walls & columns)
N	Concrete not exposed to Cl nor to freezing & thawing (footings & interior slabs, walls & columns)

$$MC = \frac{W_{AGG} - W_{OD}}{W_{OD}} \times 100 \text{ (\%)}$$

$$AC = \frac{W_{SSD} - W_{OD}}{W_{OD}} \times 100 \text{ (\%)}$$

$$EA = \frac{W_{SSD} - W_{AD}}{W_{SSD}} \times 100 \text{ (\%)}$$

$$SM = \frac{W_{WET} - W_{SSD}}{W_{SSD}} \times 100 \text{ (\%)}$$

$$BSG_{OD} = \frac{W_{OD}}{W_{SSD} - W_{SW}}$$

$$BSG_{SSD} = \frac{W_{SSD}}{W_{SSD} - W_{SW}}$$

$$ASG = \frac{W_{OD}}{W_{OD} - W_{SW}}$$